



# Amercoat 383H



High-build epoxy intermediate coating

## Product Data/ Application Instructions

- Cost effective intermediate epoxy coating
- Reduced volatile organic compounds (VOC)
- High-build and High-solids
- Tough and durable
- Also available with MIO pigmentation

### Typical uses

Amercoat 383H is used as an economic intermediate coating for atmospheric exposure in marine and industrial environments. Amercoat 383H is normally applied over an inorganic zinc-silicate or epoxy primer

### Typical Global Systems using Amercoat 383H

ISO 12944 classification	First coat	Intermediate	Finish Coat
C5	Dimetcote	Amercoat 383H	Amercoat 450 Series
C5	Amercoat 68 Series	Amercoat 383H	Amercoat 450 Series
C4	Amercoat 385PA	Amercoat 383H	Amercoat 450 Series

Amercoat 383H is not recommended for direct to metal applications, for use at continuous immersion conditions and is normally topcoated for optimal performance.

### Physical data Amercoat 383H

Finish.....	semi gloss	
Colour.....	Off White, Light Grey, Pearl Grey	
Components .....	2	
Mixing ratio (by volume) .....	1 part Resin 1 part Cure	
Curing mechanism .....	solvent release and chemical reaction between components	
Volume solids .....	77% (ISO 3233)*	
VOC.....	12% by weight	
	180 g/l	1.5 lb/gal
Dry film thickness .....	100 – 200 µm per coat 4 –8 mil per coat	
Number of coats .....	1	
Theoretical coverage		
At 100 microns/4 mil dft .....	7.7 m <sup>2</sup> /l	314 ft <sup>2</sup> /gal
At 200 microns/6 mil dft .....	3.80 m <sup>2</sup> /l	157 ft <sup>2</sup> /gal
Flashpoints .....	°C	°F
Cure .....	47	117
Resin .....	47	117
Mixed .....	47	117
Amercoat 65 .....	24	75
Amercoat 12 .....	24	75
Thinners .....	Amercoat 65	
Cleaner .....	Amercoat 12	

\* Volume solids is measured in accordance with ISO 3233. Slight variations ±3% may occur due to colour and testing variances.



# Amercoat 383H

## Chemical Resistance Guide

When applied over suitable primer or intermediate coat and topcoated with Amercoat 450 Series:

Splash and Environment	Fumes and Spillage	Weather
Acidic	Very good	Excellent
Alkaline	Very good	Excellent
Salt solutions		
Acidic	Excellent	Excellent
Neutral	Excellent	Excellent
Alkaline	Excellent	Excellent
Water	Excellent	Excellent

This table is only a guide. For specific recommendations, contact your Ameron representative for your particular corrosion protection needs.

## Surface Preparation

**PRIMED STEEL** - Coating performance is proportional to the degree of surface preparation. Refer to specifications of the specific primer being used. Prior to coating, primed surface must be clean, dry, undamaged and free of all contaminants including salt deposits. Round of all rough welds and remove weld spatter.

## Application Equipment

The following equipment is listed as a guide and suitable equipment from other manufacturers may be used. Adjustments of pressure and change of tip size may be needed to obtain the proper spray characteristics.

### AIRLESS SPRAY

Standard airless spray equipment, such as Graco, DeVilbiss, Nordson-Bede, Spee-Flo or others having a 0.019 to 0.027 inch (0.38 to 0.53 mm) fluid tip.

### CONVENTIONAL SPRAY

Industrial equipment such as DeVilbiss MBC or JGA gun with 78 or 765 air cap and "E" fluid tip and heavy mastic spring or Binks No. 18 or 62 with a 66 x 63 PB nozzle setup. Separate air and fluid pressure regulators, mechanical pot agitator and a moisture and oil trap in the main air supply line are recommended.

### MIXER

Use power mixer powered by an air motor or an explosion proof electric motor.

## Application Data

Substrate .....	Suitably primed steel coated with Amercoat 385PA, Dimetcote 9, Amercoat 68 Series	
Surface preparation.....	Primed surface must be clean, dry, undamaged and free of all contaminants including salt deposits. Round of all rough welds and remove weld spatter	
Application method.....	Airless or conventional spray.	
Environmental conditions		
Air temperature .....	5-50 °C	41-122 °F
Surface temperature.....	5-60 °C	41-140 °F

*Surface temperature must be at least 3°C / 5°F above the dew point to prevent moisture condensation on the surface.*

Potlife (°C/°F)	32/90	21/70	10/50
	1 hrs	2hrs	4 hrs

Drying times (°C/°F)	32/90	21/70	10/50
Dry to touch .....	3 hrs	6 hrs	10 hrs
Dry through.....	10 hrs	16 hrs	24 hrs

Recoat or topcoat times (°C/°F)	32/90	21/70	10/50
Minimum .....	10 hrs	16 hrs	24 hrs
Maximum with epoxies and with Amercoat 450 Series....	30 days		

*Maximum recoating/topcoating time intervals are dependent on temperature, degree of weathering, type of topcoat, and service conditions of the complete coating system. Consult your Ameron representative for specific recommendations.*

*Drying times are dependent on temperature, ventilation and film thickness.*

# Amercoat 383H



## Application Procedure

Amercoat 383H is packaged in the proper mixing proportions of resin and cure.

Resin            10 L (2.6 gal) in 20 L can  
Cure             10 L (2.6 gal) in 10L can  
Thinner:        Amercoat 65  
Cleaner:        Amercoat 12

1. Flush equipment with recommended cleaner before use.
2. Stir resin (in the larger container) to an even consistency with a power mixer.
3. Add cure to resin and stir to an even consistency. NOTE: Since the potlife is limited and shortened by high temperatures, do not mix more material than will be used within the potlife period.
4. If thinning is necessary for workability do not add more than 10% of recommended thinner.
5. Stir during application to maintain uniformity of material. Apply a wet even coat in parallel passes. Overlap each pass 50% to avoid bare areas, pinholes or holidays.
6. Double coat all welds, rough spots, sharp edges and corners, rivets, bolts, etc.
7. Application at 170  $\mu\text{m}$  wet film thickness will normally provide 125  $\mu\text{m}$  dry.
8. Check thickness of dry coating with a non-destructive dry film thickness gauge, such as Mikrotest or Elcometer. If less than specified thickness, apply additional material as needed.
9. Small damaged or bare areas and random pinholes or holidays can be touched up by brush. Repair larger areas by spray.
10. In confined areas ventilate with clean air during application and drying until all solvents are removed. Temperature and humidity of ventilating air must be such that moisture condensation will not form on surface.
11. Clean all equipment with recommended cleaner immediately after use or at least at the end of each working day or shift. When left in spray equipment, the product will cure and cause clogging.

## Shipping Data

Packaging  
Resin ..... 10 L (2.6 gal) in 20 L can  
Cure ..... 10 L (2.6 gal) in 10 L can

Shipping weight	kg	lb
Resin .....	approx. 18	40
Cure .....	approx. 16	36

Shelf life  
Resin and cure..... 1 year from shipment date when stored indoors in unopened, original containers at 5 to 40°C (41 to 104°F)

## Caution

This product is flammable. Keep away from heat and open flame. Keep container closed. Use with adequate ventilation. Avoid prolonged and repeated contact with skin. If used in confined areas, observe the following precautions to prevent hazards of fire or explosion or damage to the health:

1. circulate adequate fresh air continuously during application and drying;
2. use fresh air masks and explosion proof equipment;
3. prohibit all flames, sparks, welding and smoking.

Do not empty into drains. Take precautionary measures against static discharges. For specific information on hazardous ingredients, required ventilation, possible consequences of contact and safety measures see Safety Data Sheet.

## Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with application instructions must be observed during all storage, handling, use and drying periods.

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

## Warranty

Ameron warrants its products to be free from defects in material and workmanship. Ameron's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at Ameron's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-confirming products. Any claim under this warranty must be made by Buyer to Ameron in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Ameron of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

**Ameron makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall Ameron be liable for consequential or incidental damages.**

Any recommendations or suggestion relating to the use of the products made by Ameron, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole descretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

## Limitation of Liability

Ameron's liability on any claim of any kind, including claims based upon Ameron's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim.

In no event shall Ameron be liable for consequential or incidental damages.

## Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.