



Amercoat 4182

High Build Modified Urethane-Alkyd

(Formerly Colourclad Finish 2300)

Product Data/ Application Instructions

- **Single pack semi-gloss urethane-alkyd finish**
- **EPA compliant (1998) as a top coat to PG6/ 23**
- **Good colour and gloss retention**
- **Excellent durability**
- **Quick and easy to apply**

Typical Uses

Durable finish for Amercoat re-paint systems for pre-coated cladding.

Mixing

Stir thoroughly before use until the product is uniform throughout.

Overcoating

Can be overcoated with itself to increase the coating thickness. Certain strong colours may require more than one coat for full opacity.

Physical Data

Appearance when dry	semi gloss as standard		
Colour	RAL and BS*		
Components	1		
Volume solids	50 ± 2%		
VOC	408 g/l		
Curing mechanism	solvent release and reaction with oxygen from the air		
	typical	minimum	maximum
Dry film thickness (µm)	50	40	60
Wet film thickness (µm)	100	80	120
(Wet film thicknesses quoted are theoretical for one airless spray coat)			
Theoretical coverage	10.0 m ² /l (at typical dft)		
Specific gravity	approx 1.1 kg/l (depending on colour)		
Flashpoint			
(closed cup)	°C	°F	
Amercoat 4182	40	104	
Amercoat 15	38	100	

*Reference is made to the basic colour collections of RAL and BS-4800.

Amercoat 4182

Surface Preparation

Applied over surfaces primed typically with Amercoat 4180 or Amercoat 4181 single pack primers. The priming system and preparation will depend on the type and condition of the substrates. Consult your Ameron representative for detailed specifications. All surfaces must be dry and free of dust, salts, grease and other contaminants immediately before coating.

Application Methods

AIRLESS SPRAY - Tip size 15-17 thou' (0.38-0.43mm). Pressure at tip 2800 psi (200 kg/cm²).

BRUSH/ROLLER - Apply evenly using a clean, well loaded brush or roller.

At low temperatures may be thinned with up to 5% by volume of the recommended thinner to ease application.

Application Data

Substrate primed substrates
Application methods airless spray, brush, roller
Potlife (at 20°C/68°F) not applicable

Environmental Conditions

Amercoat 4182 should only be applied within the limits of temperature and humidity set out below.

Relative humidity: up to 90%
Surface temperature: minimum: 5°C/41°F
..... maximum: 40°C/104°F

The surface temperature must also be at least 3°C/5°F above dew point

Drying Characteristics

Temperature °C/°F	10/500	20/68	30/86
Touch dry	4 hours	2 hours	1 hour
Hard dry	16 hours	8 hours	6 hours
Overcoating (minimum)	16 hours	8 hours	6 hours
Overcoating (maximum)	No maximum overcoating time when overcoating with itself		

NOTE: drying and curing times are dependent on air and substrate temperature, applied film thickness, ventilation and other environmental conditions. Times are shorter at higher temperatures and longer at lower temperatures

Thinner Amercoat 15

Cleaner Amercoat 15

Amercoat 4182

Application procedure

1. Flush equipment with recommended cleaner before use.
2. Stir the contents of the can to an even consistency.
3. Thinning is normally not required for airless spray.
4. Stir during application to maintain uniformity of material. When spraying, apply a wet even coat in parallel passes. Overlap each pass 50% to avoid bare areas, pinholes or holidays.
5. Double coat all rough spots, sharp edges and corners, rivets, bolts, etc.
6. Application at 100 µm wet film thickness will normally provide 50 µm dry film.
7. Check thickness of dry coating with a non-destructive dry film thickness gauge, such as Mikrotest or Elcometer. If less than specified thickness, apply additional material as needed.
8. Small damaged or bare areas and random pinholes or holidays can be touched up by brush. Repair larger areas by spray.
9. In confined areas ventilate with clean air during application and drying until all solvents are removed. Temperature and humidity of ventilating air must be such that moisture condensation will not form on surface.
10. Clean all equipment with recommended cleaner immediately after use or at least at the end of each working day or shift

Before using the product, read the label on the can and consult the material safety data sheet.

Shipping Data

Pack size	5 litres
Shipping weight.....	approx. 6.5 kg
Shelf life	1 year from shipment date or as indicated on label when stored indoors in unopened, original containers at 5 to 40°C (41 to 104°F).

Amercoat 4182

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

Ameron warrants its products to be free from defects in material and workmanship. Ameron's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at Ameron's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to Ameron in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Ameron of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

Ameron makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall Ameron be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by Ameron, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

Ameron's liability on any claim of any kind, including claims based upon Ameron's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim.

In no event shall Ameron be liable for consequential or incidental damages.

Due to Ameron's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the Ameron Performance Coatings & Finishes website at www.amerondirect.co.uk

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.