



Enfield Routemaster 9503

Water borne acrylic road marking paint

Product Data/ Application Instructions

- **Fast drying time**
- **Low volatile organic compounds**
- **Skid resistant**
- **May be directly applied to virgin black top**
- **Tested to BS 6044 performance standard**
- **Resistant to diesel spillage**
- **90% luminance for the white line**

Typical Uses

Suitable for use on:

- Virgin black top, old black top
- Concrete, wood, brick, paving and existing painted lines
- Roads, airports, airfield runways, car parks,
- Factories and sports facilities.

Overcoating

Can be overcoated with itself and other products from the Enfield Routemaster range if necessary. Before using the product, read the label on the can and consult the material safety data sheet.

Physical Data

Appearance when dry	matt		
Colour	white and yellow		
Components	1		
Volume solids	60 ± 3%		
VOC	104 g/l		
Curing mechanism	physical drying		

	typical	minimum	maximum
Dry film thickness (µm)	120	110	135
Wet film thickness (µm)	200	183	225
(Wet film thicknesses quoted are theoretical for one machine application)			
Theoretical coverage	up to 100 metres of 5 cm		
(at typical dft)	line per litre (330ft of 2 inch line per litre)		
Specific gravity	1.7 kg/l.		
Flashpoint (closed cup)	Not applicable		

Enfield Routemaster 9503

Surface Preparation

VIRGIN BLACKTOP -This product may be applied directly to this substrate as bitumen bleed is minimised.

EXISTING SOUND COATINGS - Roughen surface mechanically to provide a “key” for the new coating.A test patch is recommended to confirm suitability.

Enfield Routemaster 9503 is not recommended for application over existing thermoplastic lines, particularly where there is a high presence of Ballotini beads.

SYNTHETIC ALL WEATHER SURFACES - Check compatibility prior to use.

CONCRETE – Substrate should be sound and free from laitence.

NOTE - All surfaces must be dry and free of dust, salts, grease and other contaminants immediately before overcoating.

Application Methods

MACHINE APPLICATION - is recommended in order to obtain the maximum coverage, film thickness and consistency of line. Do not thin the coating

BRUSH - Apply evenly using a clean, well loaded brush; do not attempt to brush out or lay-off the wet coating otherwise correct thickness will not be achieved.

Application Data

Substrate blacktop, concrete

Application methods machine, brush

Potlife (at 20°C/68°F) not applicable

Environmental Conditions

Relative humidity: up to 90%.

(Good air movement promotes drying)

Surface temperature: minimum 7°C/45°F

..... maximum 30°C/86°F

The surface temperature must also be at least 3°C/5°F above the dew point.

Drying Characteristics

Temperature 20°C/68°F

Touch dry 10 minutes

Hard dry 16 hours

Full cure 48 hours

Overcoating (minimum) 2 hours

Overcoating (maximum) -

Thinner normally not necessary

Cleaner water

Enfield Routemaster 9503

Mixing

Stir thoroughly before use until the product is uniform throughout.

Shipping Data

Pack size 5 litres

Shipping weight approx. 9.5 kg

Shelf life 1 year when stored indoors in unopened, original containers at 5 to 35°C (41 to 95°F). Do not allow to freeze

Reflectivity To reflectorise, apply Ballotini glass beads 9618 to the wet film at a rate of 400g per square metre.

Enfield Routemaster 9503

Safety

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

Warranty

Ameron warrants its products to be free from defects in material and workmanship. Ameron's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at Ameron's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to Ameron in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Ameron of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

Ameron makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall Ameron be liable for consequential or incidental damages.

Any recommendations or suggestion relating to the use of the products made by Ameron, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

Limitation of Liability

Ameron's liability on any claim of any kind, including claims based upon Ameron's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim.

In no event shall Ameron be liable for consequential or incidental damages.

Due to Ameron's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the Ameron Performance Coatings & Finishes website at www.amerondirect.co.uk

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

Condition of Sale

All our transactions are subject to our Terms and Conditions of Sale.