



# Enfield Routemaster 9623

## Two pack epoxy road marking paint

### Product Data/ Application Instructions

- **Good medium for high reflectivity**
- **Resistant to abrasion**
- **Superior chemical resistance**
- **Superior fuel resistant**
- **Excellent adhesion to Alkaline surfaces such as concrete**

#### Typical Uses

Line marking paint for:  
Old black top, concrete, wood, brick, paving and certain existing thermoplastic and lines. Roads, airport and airfield runways. Car parks, factories and sports facilities.

#### Overcoating

Can be overcoated with itself if necessary. Surface must be abraded if overcoating after maximum overcoating time has elapsed.  
Before using the product, read the label on the can and consult the material safety data sheet.

#### Physical Data

Appearance when dry .....	sheen		
Colour .....	white and yellow		
Components .....	2		
Mixing ratio by volume.....			
Resin .....	4.75 parts		
Cure .....	1 part		
Volume solids .....	60 ± 3%		
VOC .....	400 g/l		
Curing mechanism .....	solvent release and chemical reaction between components. Effective cure down to 10°C/50°F.		
	<b>typical</b>	<b>minimum</b>	<b>maximum</b>
Dry film thickness (µm)	160	100	200
Wet film thickness (µm)	267	167	333
(Wet film thicknesses quoted are theoretical for one machine application)			
Theoretical coverage .....	up to 75 metres of 5 cm		
(at typical dft)	line per litre (248ft of 2 inch line per litre)		
Specific gravity .....	1.6 kg/l (mixed product)		
Flashpoint			
(closed cup) .....	°C	°F	
Resin.....	25	77	
Cure .....	28	82	
Amercoat 12 .....	24	75	

# Enfield Routemaster 9623

---

## Surface Preparation

BLACKTOP - May be applied to blacktop at applicators discretion, however, Ameron Coatings recommend a sealer coat Enfield Routemaster 9503 is applied prior to use of Enfield Routemaster 9623.  
SYNTHETIC ALL WEATHER SURFACES - Check compatibility prior to use.

EXISTING THERMOPLASTIC - Check compatibility prior to use.

CONCRETE – Substrate should be sound and free from laitence.

NOTE - All surfaces must be dry and free of dust, salts, grease and other contaminants immediately before coating.

## Application Methods

MACHINE APPLICATION - is recommended in order to obtain the maximum coverage, film thicknesses and consistency of line. Do not thin the coating. Ensure surface is clean and dry.

BRUSH - Apply evenly using a clean, well loaded brush; do not attempt to brush out or lay-off the wet coating otherwise correct thickness will not be achieved.

## Application Data

Substrate ..... concrete, blacktop

Application methods ..... machine, brush

Potlife (at 20°C/68°F) ..... 8 hours

### Environmental Conditions

Relative humidity: ..... up to 90%.

Surface temperature: ..... minimum 10°C/50°F

..... maximum 35°C/95°F

The surface temperature must also be at least 3°C/5°F above the dew point.

Prior to the use of Enfield Routemaster 9623 in hot climates, where surface temperature is likely to exceed 30°C/86°F for long periods, consult your Ameron representative for specific technical advice

### Drying Characteristics

Temperature ..... 20°C/68°F

Touch dry ..... 6 hours

Hard dry ..... 24 hours

Full cure ..... 5 days

Overcoating (minimum) ..... 4 hours

Overcoating (maximum) ..... 5 days

NOTE: drying and curing times are dependent on air and steel temperature, applied film thickness, ventilation and other environmental conditions. Times are shorter at higher temperatures and longer at lower temperatures.

Thinner ..... normally not necessary

Cleaner ..... Amercoat 12

# Enfield Routhemaster 9623

---

## Mixing

Stir the resin component thoroughly, then add the cure and continue mixing until the product is uniform throughout. A powerful mixer should be used.

## Shipping Data

### Shipping weight

Resin.....	approx. 33 kg (20l unit)
Cure .....	approx. 4 kg (20l unit)
Resin.....	approx. 9 kg ( 5l unit)
Cure .....	approx. 1 kg ( 5l unit)

Shelf life ..... 1 year when stored indoors in unopened, original containers at 5 to 35°C (41 to 95°F).

Reflectivity ..... To reflectorise, apply Ballotini glass beads 9618 to the wet film at a rate of 400g per square metre.

# Enfield Routemaster 9623

---

## **Safety**

Since improper use and handling can be hazardous to health and cause of fire or explosion, safety precautions included with Product Data/Application Instruction and Material Safety Data Sheet must be observed during all storage, handling, use and drying periods.

## **Warranty**

Ameron warrants its products to be free from defects in material and workmanship. Ameron's sole obligations and Buyer's exclusive remedy in connection with the products shall be limited, at Ameron's option, to either replacement of products not conforming this warranty or credit to Buyer's account in the invoiced amount of the non-conforming products. Any claim under this warranty must be made by Buyer to Ameron in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify Ameron of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

**Ameron makes no other warranties concerning the product. No other warranties, whether express, implied or statutory, such as warranties of merchantability or fitness particular purpose, shall apply. In no event shall Ameron be liable for consequential or incidental damages.**

Any recommendations or suggestion relating to the use of the products made by Ameron, whether in its technical literature, or response to specific enquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyer's having requisite skill and know-how in the industry, and therefore it is Buyer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. Variation in environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

## **Limitation of Liability**

Ameron's liability on any claim of any kind, including claims based upon Ameron's negligence or strict liability, for any loss or damage arising out of, connected with, or resulting from the use of the products, shall in no case exceed the purchase price allocable to the products or part thereof which give rise to the claim.

In no event shall Ameron be liable for consequential or incidental damages.

Due to Ameron's policy of continuous product improvement, the information contained in this Product Data/Application Instructions sheet is subject to change without notice. It is the Buyer's responsibility to check that this issue is current prior to using the product. For the most up-to-date Product Data/Application Instructions always refer to the Ameron Performance Coatings & Finishes website at [www.amerondirect.co.uk](http://www.amerondirect.co.uk)

To avoid any confusion that may arise through translation into other languages, the English version of the Product Data/Application Instructions will be the governing literature and must be referred to in case of deviations with product literature in other languages.

## **Condition of Sale**

All our transactions are subject to our Terms and Conditions of Sale.